

SHANGHAI VANA BIOTECH CO., LTD.

http://www.vanabio.com

Add:203 Room,2 Build, No. 1588 of Huhang Road , Shanghai City, China.

SILIT-3200

TECHNICAL DATA SHEET

Introduction

SILIT-3200 is a kind of high concentration block amino silicone softener, the product can be used as various textiles finishing agent (such as cotton and its blends, rayon, viscose fiber, synthetic fiber, silk, wool, etc). Especially suited for blends fabrics. **SILIT-3200** have good smooth and fluffy handfeeling.

Characteristics

Appearance:	Transparent yellow liquid
pH value:	7~9(1% Aqueous solution)
Solid content:	100%
Ionic Character:	Light cationic
Diluent:	Water
Compatibility:	Be mixed easily with cationic and nonionic auxiliaries

Features of products

- Provides a high level of smooth.
- Very low yellowing.
- Excellent product stability.
- Provides dilutions that have excellent compatibility with conventional textile auxiliaries.

Applications

Emulsifying process:

SILIT-3200 <100% solid content> emulsified to 30% solid content cationic emulsion

 SILIT-3200 ----240g +TO5 ----30g +TO7 ----30g BCS ----12g

Stirring 10minutes

2 slowly +H₂O ----200g; then stirring 30minutes

(3) slowly +HAc (----24g) + H_2O (----200g); then slowly add the mixture and stirring 15min

(4) +H₂O ----364g; then stirring 15minutes

Ttl.: 1000g / 30% solid content



http://www.vanabio.com

Add:203 Room,2 Build, No. 1588 of Huhang Road , Shanghai City, China.

1.Exhaustion process:

SILIT-3200 (30%,after 1~3%o.w.f.

dilution)

1 0/00.000

Usage :40°C~50°C×15~30min

2.Padding process:

SILIT-3200(30%,after 10~30g/L

dilution)

Usage :once-dip-once-nip

Package

SILIT-3200 is available in 200kg plastic drums.

Storage and shelf-life

When stored in its original packaging at a temperature of between -20°C and +50°C, **SILIT-3200** may be stored for up to 12 months from its date of manufacture (expiry date). Comply with the storage instructions and expiry date marked on the packaging. Past this date, **Shanghai Vana Biotech** no longer guarantees that the product meets the sales specifications.